

LOXIAMID PA66 CF15GF15 FRV0 HS1 04065 | PA66

T E C H N I C A L D A T A S H E E T
P R O V I S I O N A L

DESCRIPTION

LOXIAMID PA66 CF15GF15 FRV0 HS1 04065 is 30% carbon Fiber and Glass Fiber Reinforced an injection molding grade of electrically conductive, flame retardant, Polyamide 66 resin.

FEATURES

- Electrically Conductive
- High Dimensional Stability
- Easy Processing Characteristics
- High Stiffness and Rigidity
- Good Mold Release Characteristics.

APPLICATIONS

- Mining Rolls
- Electrically Conducting Parts

PROPERTY, Test Conditions	Standard	Unit	Value
MECHANICAL			
Tensile Strength at Break	ISO 527	MPa	165
Elongation at Break	ISO 527	%	1.5
IMPACT			
Izod Notched Impact	ISO 180	kJ/m ²	9
PHYSICAL			
Density	ISO 1183	g/cm ³	1.56
THERMAL			
Heat Deflection Temperature @ 1.8 MPa	ISO 75	°C	245
FLAMMABILITY			
Flammability Rating, 1.6mm	UL 94	-	V0
Flammability Rating, 3.2mm	UL 94	-	V0

PROCESSING	Unit	Value
PARAMETER		
Drying Temperature	°C	80
Drying Time	hrs	2 – 4
Melt Temperature	°C	270 – 300
Mold Temperatures	°C	70 - 110

DISCLAIMER

GENERAL INFORMATION

The information specified on this product data sheet and the accompanying safety data sheet correspond to our current level of understanding and experience.

The user/processor bears responsibility for ensuring that the product described here is suited for the intended applications and that the application/processing complies with the necessary statutory provisions. The user/processor is to ensure that he/she is in possession of the current version of the product data sheet and the safety data sheet. This can be requested from the account manager known to the user/processor.

We prohibit the complete or partial adoption of information and formulations from this product data sheet.

PRODUCT PROPERTIES

The indicated test values represent approximate values but are not binding maximum or minimum values. It is possible that the values may be influenced or may deviate due to tool design, processing conditions, etc. The test values do not represent any contractual assurances regarding the properties or the suitability of the product for a specific intended application.

All of the information, approximate values, descriptions, drawings, etc. included in the product data sheet can change at any time and do not represent any contractually agreed properties of our product.

PRODUCT SAFETY

As long as the processing of our product is carried out in compliance with the processing instructions specified in the product data sheet, molten masses are thermally stable and are not a source of any danger due to molecular decomposition or the formation of gases or vapor.

According to the safety data sheet the user/processor is to ensure compliance with the specified occupational exposure limits through sufficient exhaust and ventilation in order to avoid any negative impact on the health and well-being of his/her employees. If processing is carried out at temperatures significantly below the specified processing temperatures then gaseous products of decomposition can form as a result of the partial decomposition of the polymer. Further information about this can be found in the safety data sheet.

PRODUCT PROCESSING

The application, use and processing as well as further processing of our products and of products manufactured by the user/processor is carried out beyond the scope of our control and is the sole responsibility of the user/processor. The user/processor is to conduct his/her own tests and studies regarding the suitability of the product described here for the intended applications.

Please note that our products are not suited for use with or the processing of medical products.

Revision: December 2018

LOXIM INDUSTRIES LIMITED

India | Germany | USA

LOXIMTM
infinite possibilities. finite results.