

LOXIPULP

DIRECT DYES • BASIC DYES • REACTIVE DYES

Product Family	Loxim Grade Description	Property (Liquid Form)					Fastness Properties (PA) Fastness Scale - Light Fastness : 8 Excellent, 1 Poor Others: 5 Excellent, 1 Poor							Typical Applications
		Liquid	Powder	Specific Gravity	Viscosity (mPas)	pH	Light	Water	Ammonia (10%)	Chlorine (2gpl)	Sulfuric Acid (5%)	Caustic Soda (2.5%)	Sodium Carbonate (10%)	
Paper Dyes	Loxipulp Yellow 6GP	•		1.0-1.2	<200	8-10	4-5	4-5	5	4-5	5	5	5	Pulp , Paper Finishing
	Loxipulp Yellow US	•		1.0-1.2	<200	8-10	4-5	4	4-5	4-5	4-5	4	4	Pulp , Paper Finishing
	Loxipulp Yellow KC	•	•	1.0-1.2	<200	8-10	5-6	5	4-5	4-5	2-3	5	4-5	Pulp , Paper Finishing
	Loxipulp Yellow Y	•	•	1.0-1.2	<200	8-10	4	5	4-5	4-5	3	4-5	4-5	Pulp , Paper Finishing
	Loxipulp Yellow 6G	•	•	1.0-1.2	<200	8-10	4-5	4-5	5	4-5	4-5	4-5	4-5	Pulp , Paper Finishing
	Loxipulp Yellow 6R-Z	•		1.0-1.2	<200	8-10	3-4	4-5	4-5	4	3	4-5	4-5	Pulp , Paper Finishing
	Loxipulp Orange MD		•	1.0-1.2	-	8-10	4-5	4-5	4-5	4-5	4	2	4-5	Pulp , Paper Finishing
	Loxipulp Red F3B	•		1.0-1.2	<200	8-10	4-5	4-5	4-5	4	2-3	5	4-5	Pulp , Paper Finishing
	Loxipulp Red 5B	•	•	1.0-1.2	<200	8-10	5	5	4-5	2	5	5	3-4	Pulp , Paper Finishing
	Loxipulp Red CAS	•	•	1.0-1.2	<200	8-10	4-5	5	4-5	2	5	5	3-4	Pulp , Paper Finishing
	Loxipulp Red P	•	•	1.0-1.2	<200	8-10	4	5	4-5	4	4	2	4	Pulp , Paper Finishing
	Loxipulp Red 2B	•		1.0-1.2	<200	8-10	4-5	3-4	4	1-2	4-5	3-4	4-5	Pulp , Paper Finishing
	Loxipulp Green BLL		•	1.0-1.2	-	8-10	5-6	5	5	3	4	1-2	4-5	Pulp , Paper Finishing
	Loxipulp Blue BRR	•	•	1.0-1.2	<200	8-10	4-5	3-4	4	1-2	4-5	3-4	4-5	Pulp , Paper Finishing
	Loxipulp Blue 2RL	•	•	1.0-1.2	<200	8-10	4	3-4	4	3-4	4	4	4	Pulp , Paper Finishing
	Loxipulp Brill Blue RF	•		1.0-1.2	<200	8-10	4	5	4-5	4	3-4	4	4-5	Pulp , Paper Finishing
Loxipulp Blue 2RF	•		1.0-1.2	<200	8-10	4	5	4-5	4-5	4	4	4-5	Pulp , Paper Finishing	

LOXIPULP

DIRECT DYES • BASIC DYES • REACTIVE DYES

Product Family	Loxim Grade Description	Property (Liquid Form)					Fastness Properties (PA) Fastness Scale - Light Fastness : 8 Excellent, 1 Poor Others: 5 Excellent, 1 Poor							Typical Applications
		Liquid	Powder	Specific Gravity	Viscosity (mPas)	pH	Light	Water	Ammonia (10%)	Chlorine (2gpl)	Sulfuric Acid (5%)	Caustic Soda (2.5%)	Sodium Carbonate (10%)	
Paper Dyes	Loxipulp Blue KSR		•	1.0-1.2	-	8-10	4	3-4	4	3-4	4	4	4	Pulp , Paper Finishing
	Loxipulp Brill Violet 5RS	•		1.0-1.2	<100	8-10	5-6	5	5	2	5	4	4-5	Pulp , Paper Finishing
	Loxipulp Brown SBR	•		1.0-1.2	<200	9-11	4-5	4-5	5	2	5	4	4-5	Pulp , Paper Finishing
	Loxipulp Black BSN	•		1.0-1.2	<200	8-10	4-5	5	5	1-2	4-5	2	5	Pulp , Paper Finishing
	Loxipulp Red HE3B	•		1.0-1.2	<200	8-10	4-5	4-5	3	1-2	4-5	2	4	Pulp , Paper Finishing
	Loxipulp Brown A	•		1.0-1.2	<200	3-4	4-5	4-5	5	2	5	4	4-5	Pulp , Paper Finishing

Fastness Values	Color Change, Grey Scale
Swatch Color	Paper, Color 2%