

LOXIRECT

DIRECT DYES

Product Family	Loxim Grade Description	General Properties		Fastness Scale : 5 Excellent , 1 Poor									Typical Applications	
		Powder	Liquid	Solubility g/L @ 80 OC	Fastness Properties									
					Crocking (Dry) (AATCC 8 - 2001)	Crocking (Wet) (AATCC 8 - 2001)	Light (AATCC 16 - 2003)	Washing Test 2A (AATCC 61 - 2003)	Washing Test 1A (AATCC 61 - 2003)	Dry Cleaning (AATCC 132 - 2003)	Acidic Perspiration (AATCC 15 - 2003)	Alkaline Perspiration (AATCC 15 - 2003)		
Direct Dyes	Loxirect Yellow KC	•		100	4-5	4	4	3-4	4	4	4	4	Cotton , Paper	
	Loxirect Yellow Y	•		30	4-5	4	4	3-4	4	4	4	4	Cotton , Paper	
	Loxirect Fast Red 6BLL	•		25	4-5	4	4	4	4	4	4	4	Cotton , Paper	
	Loxirect Red F3B	•		100	4	3-4	3-4	3	3-4	4	4	4	Cotton , Paper	
	Loxirect Red 5B	•		70	4-5	3-4	3	1-2	2	4	4	4	Cotton , Paper	
	Loxirect Bordeaux 3BL	•		50	4-5	4	4-5	3-4	4	4	4	4	Cotton , Paper	
	Loxirect Red CAS	•		50	4-5	3-4	2-3	2-3	3	4	4	4	Cotton , Paper	
	Loxirect Green BLL	•		50	4	3-4	3-4	3	3-4	4	4	4	Cotton , Paper	
	Loxirect Blue 3R	•		50	4	3	4	1-2	3	4	4	4	Cotton , Paper	
	Loxirect Cyan B2B	•		50	4-5	3	1-2	3	4	4	4	4	Cotton , Paper	